



# Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: [sales@acousticalsurfaces.com](mailto:sales@acousticalsurfaces.com)

Visit our Website: [www.acousticalsurfaces.com](http://www.acousticalsurfaces.com)

**We Identify and S.T.O.P. Your Noise Problem**



130 Erick Street

Crystal Lake, IL 60014

(815) 526-0954

Final Report for:

Rendered by Manufacturer & Released to

Acoustical Surfaces, Inc.

123 Columbia Court North

Chaska, MN 55318

Test Method:

**ASTM C 1338 – 08 Standard Test Method for Determining Fungi  
Resistance of Insulation Materials and Facings**

MSL #R2011-87-2, Amendment to R2011-87

Sample Received: 3/23/11

Testing Initiated: 3/24/11

Four Week Testing Completed: 4/21/11

Final Report Issued: 4/21/11

*Judy LaZonby*

President – The MicroStar Lab, Ltd



TESTING CERT #2832.01  
ISO-R-118-02 DMK

*This laboratory is accredited in accordance with the recognized International Standard ISO IEC 17025:2005 General Requirements for the Competence of Testing and Calibration Laboratories. This accreditation demonstrates technical competence for a defined scope and the operation of a laboratory quality management system (refer to joint ISO-ILAC-IAF Connoissance dated 8 January, 2009).*

Page 1 of 4



# Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: [sales@acousticalsurfaces.com](mailto:sales@acousticalsurfaces.com)

Visit our Website: [www.acousticalsurfaces.com](http://www.acousticalsurfaces.com)

**We Identify and S.T.O.P. Your Noise Problem**



RE: ASTM C 1338  
Project # R2011-87

## Objective:

To evaluate the fungal resistance properties of one insulation material sample as seen in the ASTM C 1338 - 08 fungal resistance test.

## Test Sample Description:

1. Poly Max™ 9.4 PCF ½" (100% Polyester Acoustic Panel)

The sample was received as one larger piece from which 2 inch by 2 inch test pieces were cut. The sample was tested in triplicate for both sides of the sample.

## Customer Requested Modifications

None

## Procedure:

Inoculum was prepared using working fungal stock cultures that had been incubating for 5 days or longer on Potato Dextrose Agar. The test includes the following fungi:

1. *Aspergillus niger* ATCC # 9642
2. *Penicillium funiculosum* ATCC # 11797
3. *Aspergillus flavus* ATCC # 9643
4. *Aspergillus versicolor* ATCC # 11730
5. *Chaetomium globosum* ATCC # 6205

Each fungal culture was adjusted in concentration to  $1.0 \times 10^6 \pm 200,000$  spore/mL. Equal volumes of each adjusted fungal suspension were blended for the final mixed spore suspension. Each test piece was placed into a separate sterile Petri dish. The test pieces were allowed to precondition in the test chamber at  $30 \pm 2^\circ\text{C}$  and  $95 \pm 4\%$  relative humidity for 4 hours prior to testing. After pre-conditioning, the test pieces were evenly inoculated with the mixed spore suspension using a sterile sprayer. Inoculated samples were then placed into the test chamber maintained at  $30 \pm 2^\circ\text{C}$  and  $95 \pm 4\%$  relative humidity for 28 days. At the end of the incubation period, samples were examined at 40X magnification for the presence of fungal growth. A comparative item was not submitted by the customer, therefore the test criteria is growth or no growth of fungus.

Individual viability plates of each test organism were prepared by placing approximately 0.2 mL of the prepared spore suspension onto Potato Dextrose Agar. Sterile filter paper was placed onto the surface of Potato Dextrose agar and inoculated with the mixed spore suspension as an inoculum viability control. A sterile tongue blade was also inoculated with the blended spore suspension as a viability control. See results below.



TESTING CERT #2832.01  
ISO-R-118-02 DMK

This laboratory is accredited in accordance with the recognized International Standard ISO/IEC 17025:2005 General Requirements for the Competence of Testing and Calibration Laboratories. This accreditation demonstrates technical competence for a defined scope and the operation of a laboratory quality management system (refer to joint ISO-ILAC-IAF Communiqué dated 5 January, 2009).

Page 2 of 4



# Acoustical Surfaces, Inc.

**SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS**

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: [sales@acousticalsurfaces.com](mailto:sales@acousticalsurfaces.com)

Visit our Website: [www.acousticalsurfaces.com](http://www.acousticalsurfaces.com)

## We Identify and **S.T.O.P.** Your Noise Problem



RE: ASTM C 1338

Project # R2011-87

Relative humidity and temperature measurement equipment are validated using a Vaisala Thermohygrometer and Probe, MI70/ HMP75B that is externally calibrated to NIST traceable standards. Relative humidity is internally validated using NIST traceable K<sub>2</sub>SO<sub>4</sub> saturated salts that are externally calibrated by an ISO/IEC 17025 FINAS accredited laboratory, Certificate # K008-U00038. Temperature is internally validated using a Cole Palmer Thermometer, Model 90250-31, Serial # 4463 that is externally calibrated by an ISO/IEC 17025 A2LA accredited laboratory, Calibration Certificate # 1681.02. An internally validated Veriteq data logger, Serial # 09102083, was also used to verify pre-condition parameters.

### Test Results:

After 4 weeks of incubation in the C 1338 chamber, the results for the test pieces can be found in the data table below. The samples were rated according to the scales below. The test controls performed as expected, confirming the validity of the test. Individual test organism controls confirmed the viability of each test organism used. These results pertain only to the samples tested.

<b>Interpretation of results according to C 1338 – 08 test method</b>
Growth greater than that on the comparative item shall be considered to have failed
Growth not greater than that on the comparative item shall be considered to have passed.
If no growth is the criterion, any growth shall be considered a failure

Since no comparative item was supplied by the customer, the criterion used to determine Pass/Fail for this test was “growth/no growth” criterion.

Sample	Description of Growth	Pass/Fail
Poly Max™ 9.4 PCF ½” (100% Polyester Acoustic Panel)	No fungal growth found on all three replicates at 40X magnification	PASS



TESTING CERT #2832.01  
ISO-R-118-02 DMK

This laboratory is accredited in accordance with the recognized International Standard ISO/IEC 17025:2005 *General Requirements for the Competence of Testing and Calibration Laboratories*. This accreditation demonstrates technical competence for a defined scope and the operation of a laboratory quality management system (refer to joint ISO-ILAC-IAF Communiqué dated 5 January 2009).

Page 3 of 4



# Acoustical Surfaces, Inc.

**SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS**

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: [sales@acousticalsurfaces.com](mailto:sales@acousticalsurfaces.com)

Visit our Website: [www.acousticalsurfaces.com](http://www.acousticalsurfaces.com)


**We Identify and S.T.O.P. Your Noise Problem**



RE: ASTM C 1338  
Project # R2011-87



Pictured above are the three replicates tested of sample Poly Max™ 9.4 PCF ½” (100% Polyester Acoustic Panel) and the test controls in the test chamber at Day 21.



The picture on the left is of the sterile tongue blade control at Day 28 which was inoculated with the test inoculum. The picture on the right is of the sterile paper strips at Day 28 that were placed on the agar surface and inoculated with the test inoculum. Both inoculum controls verify that the test inoculum was appropriate and viable.



TESTING CERT #2832.01  
ISO-R-118-02 DMK

This laboratory is accredited in accordance with the recognized International Standard ISO/IEC 17025:2005 *General Requirements for the Competence of Testing and Calibration Laboratories*. This accreditation demonstrates technical competence for a defined scope and the operation of a laboratory quality management system (refer to joint ISO-ILAC-IAF Communiqué dated 5 January, 2009).

Page 4 of 4

- Soundproofing Products • Sonex™ Ceiling & Wall Panels • Sound Control Curtains • Equipment Enclosures • Acoustical Baffles & Banners • Solid Wood & Veneer Acoustical Ceiling & Wall Systems
- Professional Audio Acoustics • Vibration & Damping Control • Fire Retardant Acoustics • Hearing Protection • Moisture & Impact Resistant Products • Floor Impact Noise Reduction
- Sound Absorbers • Noise Barriers • Fabric Wrapped Wall Panels • Acoustical Foam (Egg Crate) • Acoustical Sealants & Adhesives • Outdoor Noise Control • Assistive Listening Devices
- OSHA, FDA, ADA Compliance • On-Site Acoustical Analysis • Acoustical Design & Consulting • Large Inventory • Fast Shipment • No Project too Large or Small • Major Credit Cards Accepted