



Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: sales@acousticalsurfaces.com

Visit our Website: www.acousticalsurfaces.com

*We Identify and **S.T.O.P.** Your Noise Problem*

Encore™

22 oz. 64" / 15 oz. 62" WIDE • 100% POLYESTER
22 oz. INHERENTLY FLAME RETARDANT / 15 oz. DURABLY FLAME RETARDANT



ENCORE™ 22 oz. / 64" WIDE CABERNET



ENCORE™ 15 oz. / 62" WIDE BLACK



WHITE



BEIGE



ROSETTA



IRIS



PEWTER



CORONA



ICE BLUE



ROYAL BLUE



PROVINCIAL



CYPRESS



CRIMSON



PLUM



CABERNET



ESPRESSO

Continued on next page...



Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: sales@acousticalsurfaces.com

Visit our Website: www.acousticalsurfaces.com

We Identify and S.T.O.P. Your Noise Problem

ENCORE FABRIC SPECIFICATIONS

QUALITY	22 oz. VELOUR	15 oz. VELOUR
COMPOSITION:	100% polyester	100% polyester
WIDTH:	64 (162 cm)	62 (157 cm)
WEIGHT:	22 oz./yd. (625 g/m)	15 oz./yd. (425 g/m)
FINISH:	Inherently Flame Retardant	Durable FR Finish
FLAME TESTING:	UFAC Class 1 NFPA 701 - Small Scale NFPA 701 - Large Scale NFPA 701 - 1996 Version California Administrative Code Title 19 Paragraph 1237.1 City of NY Bulletin No. 44	UFAC Class 1 NFPA 701 - Small Scale NFPA 701 - Large Scale NFPA 701 - 1996 Version California Administrative Code Title 19 Paragraph 1237.1 City of NY Bulletin No. 44
TEAR STRENGTH:		
Trap	Warp - 32 lbs (142 N)	Warp - 16 lbs (71 N)
(ASTM D5587)	Filling - 52 lbs (231 N)	Filling - 13 lbs (58 N)
Tongue	Warp - 5 lbs (23 N)	Warp - 4 lbs (16 N)
(ASTM D2261)	Filling - 12 lbs (53 N)	Filling - 12 lbs (53 N)
TENSILE STRENGTH:		
Grab	Warp - 60 lbs (266 N)	Warp - 64 lbs (284 N)
(ASTM D5034)	Filling - 147 lbs (653 N)	Filling - 66 lbs (293 N)
Strip	Warp - 23 lbs (102 N)	Warp - 36 lbs (160 N)
(ASTM D5055)	Filling - 100 lbs (444 N)	Filling - 40 lbs (178 N)
ABRASION:		
Wyzenbeek	Exceeds 15,000	Exceeds 15,000
(ASTM D3597)	Double Rubs	Double Rubs
Martindale	Exceeds 35,000 Cycles	Exceeds 35,000 Cycles
(ASTM D4966)		
LIGHT FASTNESS:	40 to 80 hrs (varies by color)	40 to 80 hrs (varies by color)
(ASTM D3597, Xenon)		
CROCKING:	Wet - 3 to 5 (varies by color)	Wet - 3 to 5 (varies by color)
(AATCC 107)	Dry - 3 to 5 (varies by color)	Dry - 3 to 5 (varies by color)

CARE AND CLEANING INSTRUCTIONS

1. Regular Care - Vacuum to remove ordinary lint and dust.
2. Spot Cleaning - Most spots and stains can be removed with a damp sponge, cleaning fluids, or dry cleaning powders. None of these methods should cause spotting.
3. General Cleaning - A professional dry cleaning service is recommended for on site cleaning. Supplementary flame testing is recommended after repeated dry cleaning or washings to ensure that the curtain meets local fire codes.

PATENT PENDING