



Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318

(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: sales@acousticalsurfaces.com

Visit our Website: www.acousticalsurfaces.com

We Identify and S.T.O.P. Your Noise Problems



96D Allen Blvd.,
Farmingdale, NY 11735
TEL: (631) 293-8944
FAX: (631) 293-8956
Page 1

Received: 05/23/2001	Completed: 06/14/2001	Letter: O	rb	P.O.: 508-00150	Test Report:	2-34994-0-
Client's Identification	Style: 2721 Streetwise. Fiber Content: 100% Polyester. Width: 66. Finish: 02 (water)					
Tested For:	Rendered by Manufacturer and Released to: Acoustical Surfaces, Inc. 123 Columbia Court North, Suite 201 Chaska, MN 55318	Key Test: ASTM E 84	715			
		Tel: 1-800-527-6253 Fax: 1-952-448-2613				
		CODE: 7506506005501-4				
TEST PERFORMED: ASTM E 84 – Standard Test Method for Surface Burning Characteristics of Building Materials. *						
APPROXIMATE THICKNESS OF SPECIMEN (as measured by Govmark): 0.028"						
PRODUCT CATEGORY: <input checked="" type="checkbox"/> Textile Product: <input type="checkbox"/> Non Textile Product						
* Note: Textile wallcoverings classified by this procedure are limited to use in sprinklered areas in certain public occupancies. If textile wallcoverings are used in non-sprinklered areas, a room/corner fire test is mandated.						
SPECIMEN CONDITIONING: The item tested was placed in a conditioned atmosphere of 73.4°F ± 5°F, and 50% ± 5% RH until equilibrium was reached.						
SPECIMEN MOUNTING:						
<input type="checkbox"/> Adhered: The test specimen was bonded to three 1/4" GRC (Glass Reinforced Concrete) boards (a cement asbestos substitute) to form a test specimen the face of which was 20" x 24".						
<input checked="" type="checkbox"/> Unadhered: The 20" x 24' specimen was not adhered to any substrate. Instead, it was laid over a 2" hexagonal wire mesh screen and 1/4" rods.						
RESULTS:						
Flame Spread Index	Smoke Developed					
10	95					
CODE CLASSIFICATION SYSTEM:	Flame Spread Index	Smoke Developed				
Class I or A	0 – 25	450 or Less				
Class II or B	26 – 75	450 or Less				
Class III or C	76 – 200	450 or Less				
CONCLUSION: Based on the above Results and Code Classification System the item tested is assigned a:						
<input checked="" type="checkbox"/> Class I or A rating: <input type="checkbox"/> Class II or B rating: <input type="checkbox"/> Class III or C rating.						
REMARKS: None.						
DATA SUMMARY:						
Title to Ignition:	0.08 minutes					
Maximum Flame Spread "Distance":	2.28 feet					
Maximum Flame Spread "Time":	0.50 minutes					
CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by ASTM E 84.						
						
AUTHORIZED SIGNATURE THE GOVMARK ORGANIZATION, INC. CT jd						