Napa 2954

Yountville 9010



Sonoma 9013



Silverado 9014



Rutherford 9011



Calistoga 9012




Helena 9015

Please order a memo sample to view full scale pattern.

Napa 2954

Actual Size



Specifications

Content	100% FR polyester
Weight	13.0 ± 1.0 oz./lin. yd.
Width	72" min. useable
Repeat	26.3" vertical 18.9" horizontal
Treatment	FR antimicrobial

Cleaning Code

Standard Care Label W-S. Commercial wash at 160°F maximum wash temperature using detergents recommended for the type of washing machines being used, no chlorine bleach. Rinse warm. Do not overload the washer as this may result in inadequate cleansing of the fabric and excessive wrinkling. Dry on synthetic (cool) setting until slightly damp or just dry. Do not overload the dryer. Over-drying or drying at hot temperatures may cause unacceptable shrinkage to occur. If necessary, press with a cool iron ("polyester" or "synthetics" setting, max temp 275° F).

Performance



Colorfastness to Light (AATCC 16 Option 3) **Grade 4 min. at 60 hours**



Colorfastness to Crocking (AATCC 8)

Grade 4 min. dry & Grade 3 min. wet



Breaking Strength (ASTM D5034)

175 lbf min. warp and 90 lbf min. fill

Seam Slippage (ASTM D4034) **60 lbf min. warp and fill**



Flammability
NFPA 701 TM#1 - Pass

*ACT® registered certification mar

Miscellaneous

Every effort has been made to ensure color accuracy of the digital images, however, please order a sample before specification. Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric.

Proudly woven in the USA supporting our local communities.

Visit guilfordofmaine.com for samples.