




## Poseidon 1306



Coralline  
1294




Sea Spray  
1290




Triggerfish  
1281



Sargassum  
1296



Red Algae  
1285



Surf  
1289




Ecosystem  
1286



Beachrock  
1295




Brittle Star  
1284



Aquatic  
1291



Kelp Forest  
1287




Narwhal  
1298




King Crab  
1282




Sailfish  
1292



Tidepool  
1288



Manatee  
1299



Archipelago  
1283



Deep Blue  
1293



Java Sea  
1297



Orca  
1300

### Specifications

<b>Content</b>	90% post-consumer recycled polyester including ocean waste 10% polyester
<b>Weight</b>	18 ± 1.0 oz./lin. yd
<b>Width</b>	54" min. useable
<b>Repeat</b>	none

### Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

### Miscellaneous

- Application testing of this product is recommended.
- Colors may vary between dye lots.
- This is a directional fabric.

**Proudly woven in North America supporting our local communities.**

### Sustainability

#### OCEAN WASTE CLEAN IMPACT TEXTILES™

For every pound of fabric produced, up to half a pound of marine waste is removed from the ocean.

### SEAQUAL INITIATIVE

By partnering with the SEAQUAL INITIATIVE, we transform ocean waste into amazing textiles.

Duvaltex is an official and authorized advertiser of SEAQUAL® YARN, the SEAQUAL INITIATIVE and their related trademarks, under licence agreement. Only SEAQUAL licensees are permitted to publicly advertise details about SEAQUAL trademarks.

### Performance

- Colorfastness to light (AATCC 16.3 Option 3)**  
Grade 4 min. at 40 hours
- Colorfastness to crocking (AATCC 8)**  
Grade 4 min. dry & Grade 4 min. wet
- Breaking Strength (ASTM D5034)**  
480 lbf min. warp and 360 lbf min. fill
- Seam Slippage (ASTM D4034)**  
105 lbf min. warp and 78 lbf min. fill
- Pilling Resistance (ASTM D3511)**  
Class 4 min.
- Flammability**  
CA Technical Bulletin 117-2013 Section 1  
NFPA 260-2013 Class I
- Abrasion (ASTM D4157)**  
100,000 double rubs min. cotton duck

### Acoustical Performance

Our acoustic fabrics are all acoustically transparent. This represents the amount of sound that passes through the fabric.

**Acoustic Transparency:** 90%

For more detailed results, please consult our website.

This pattern is included in the underwriters laboratory panel fabric recognition program. Additional testing of this U.L. recognized fabric is not required on approved panels from participating manufacturers.

\*Certification Marks owned by the Association for Contract Textiles, Inc.