PANEL | ACOUSTIC

Intermix 3035

Husky 7060



Coconut 7011



Swan 7020

Foggy

7041


Seagull 7030



Rocket Ship 7010



Neptune 7040



Smoky Quartz 7061

Intermix 3035

Specifications

100% pre-consumer recycled polyester
15.3 ± 1.0 oz./lin. yd.
66" min. useable
none
polyester binder

Cleaning Code


Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup.

Bleach Cleanable - May be cleaned with a 10% bleach-to-water solution. Rinse well after cleaning. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

Acoustical Performance

The plot below summarizes impedance tube measurements of absorption of an anechoic termination and various fabrics in front of the anechoic termination.

Acoustical Performance for Panel Applications (ISO 10534-2)




NRC of anechoic termination	1.00
NRC of fabric in front of anechoic termination	.95

Performance

*	Colorfastness to Light (AATCC 16.3 Option 3) Grade 4 min. at 40 hours
U	Colorfastness to Crocking (AATCC 8) Grade 4 min. dry & Grade 3 min. wet
×	Breaking Strength (ASTM D5034) 225 lbf min. warp and fill

Sustainability

Class I or A



Flammability (ASTM E84)



Miscellaneous

Proudly woven in North America supporting our local communities.

Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric.

Visit guilfordofmaine.com for samples.



USA & INTERNATIONAL

800 544 0200 PHONE

Butter Rum

7050