Off the Grid 1233

Earthglow

Flame

Steam 1307



Solar 1313



Flora 1312



Thermal

Lava


1305

Hydro

Woodchip



Fossil 1304



Coal 1302



Tidal 1311

Off the Grid 1233

Specifications

Content	49% pre-consumer recycled polyester 38% post-consumer recycled polyester 13% polyester
Weight	10.0 ± 1.0 oz./lin. yd.
Width	66" min. useable
Repeat	none
Treatment	polyester binder


Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

Acoustical Performance

The plot below summarizes impedance tube measurements of absorption of an anechoic termination and various fabrics in front of the anechoic termination.

Acoustical Performance for Panel Applications (ISO 10534-2)



NRC of anechoic termination	1.00
NRC of fabric in front of anachoic termination	1.00

Performance

	*	Colorfastness to Light (AATCC 16.3 Option 3) Grade 4 min. at 40 hours
	Ø	Colorfastness to Crocking (AATCC 8) Grade 4 min. dry & Grade 3 min. wet
	×	Breaking Strength (ASTM D5034) 185 lbf warp and 165 lbf fill
	*	Flammability (ASTM E84) Class I or A

Sustainability




Miscellaneous

Proudly woven in North America supporting our local communities.

Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric.

This pattern is included in the underwriters laboratory panel fabric recognition program. Additional testing of this U.L. recognized component fabric is not required on approved panels from participating manufacturers.

Visit guilfordofmaine.com for samples.



† Not available in USA